

CP620S 6V 2Ah(20hr)



The rechargeable batteries are lead-lead dioxide systems. The dilute sulfuric acid electrolyte is absorbed by separators and plates and thus immobilized. Should the battery be accidentally overcharged producing hydrogen and oxygen, special one-way valves allow the gases to escape thus avoiding excessive pressure build-up. Otherwise, the battery is completely sealed and is, therefore, maintenance-free, leak proof and usable in any position.

Battery Construction


Component	Positive plate	Negative plate	Container	Cover	Safety valve	Terminal	Separator	Electrolyte
Raw material	Lead dioxide	Lead	ABS	ABS	Rubber	Copper	Fiberglass	Sulfuric acid

General Features

- Absorbent Glass Mat (AGM) technology for efficient gas recombination of up to 99% and freedom from electrolyte maintenance or water adding.
- Not restricted for air transport-complies with IATA/ICAO Special Provision A67.
- UL-recognized component.
- Can be mounted in any orientation.
- Computer designed lead, calcium tin alloy grid for high power density.
- Long service life, float or cyclic applications.
- Maintenance-free operation.
- Low self discharge.

Dimensions and Weight

Length(mm / inch).....43 / 1.69
 Width(mm / inch).....37 / 1.46
 Height(mm / inch).....83 / 3.27
 Total Height(mm / inch).....83 / 3.27
 Approx. Weight(Kg / lbs).....0.35 / 0.77



Performance Characteristics









Nominal Voltage6V
 Number of cell3
 Design Life3~5 years
 Nominal Capacity 77°F(25°C)
 20 hour rate (0.1A, 5.25V).....2Ah
 10 hour rate (0.19A, 5.25V).....1.9Ah
 5 hour rate (0.37A, 5.25V).....1.85Ah
 1 hour rate (1.46A, 4.8V).....1.46Ah
 Internal Resistance
 Fully Charged battery 77°F(25°C).....42mOhms
 Self-Discharge
 3% of capacity declined per month at 20°C(average)
 Operating Temperature Range
 Discharge-20~60°C
 Charge-10~60°C
 Storage-20~60°C
 Max. Discharge Current 77°F(25°C)30A(5s)
 Short Circuit Current100A
 Charge Methods: Constant Voltage Charge 77°F(25°C)
 Cycle use7.25-7.45V
 Maximum charging current0.8A
 Temperature compensation-15mV/°C
 Standby use6.8-6.9V
 Temperature compensation-10mV/°C

Discharge Constant Current (Amperes at 77°F25°C)

End Point Volts/Cell	5min	10min	15min	30min	1h	3h	5h	10h	20h
1.60V	7.95	5.36	3.75	2.59	1.46	0.62	0.40	0.19	0.1
1.65V	7.54	5.10	3.59	2.49	1.41	0.61	0.39	0.19	0.1
1.70V	7.11	4.84	3.41	2.38	1.35	0.58	0.38	0.19	0.1
1.75V	6.67	4.57	3.24	2.26	1.29	0.55	0.37	0.19	0.1
1.80V	6.22	4.29	3.05	2.15	1.23	0.53	0.37	0.19	0.1

Discharge Constant Power (Watts at 77°F25°C)

End Point Volts/Cell	5min	10min	15min	30min	45min	1h	2h	3h	5h
1.60V	14.5	9.79	7.46	4.29	2.96	2.56	1.64	1.22	0.80
1.65V	13.6	9.22	7.06	4.07	2.82	2.46	1.59	1.19	0.79
1.70V	12.7	8.65	6.65	3.85	2.68	2.34	1.54	1.16	0.77
1.75V	11.8	8.08	6.24	3.63	2.54	2.23	1.48	1.13	0.75
1.80V	10.9	7.51	5.82	3.40	2.39	2.11	1.42	1.09	0.74



ISO9001:2000

MH25860

G4M19906-9202-E-16

www.vision-batt.com

Shenzhen Center Power Tech. Co., Ltd.
 RM 1801, 18/F, Cangsong Bldg., Terra 6 Rd, Chegongmiao, Futian District, Shenzhen 518040 China
 Tel: (+86-755) 8343 5688 Fax: (+86-755) 8384 9585 E-mail: sales@vision-batt.com